



50 PROFESSIONAL-GRADE POLYMER- MODIFIED MORTAR

DESCRIPTION

Flextile 50 is a professional-grade, high-performance, one-component, polymer-modified thin-set mortar.

Unique, high polymer modification provides the superior bonding characteristics and improved flexibility for installation of tile and stone over most surfaces.

BASIC USES

Installation of ceramic and porcelain tile, quarry tile, pavers, and many types of marble, granite and natural stone.

RECOMMENDED SURFACES

- Interior or exterior floor and wall installations*.
- Vertical or horizontal surfaces of concrete, masonry, terrazzo, cement backer boards.
- Existing surfaces of properly prepared tile, stone or cementitious terrazzo.
- Exterior grade plywood or gypsum board, in interior dry areas only.
- Existing surfaces of properly prepared non-cushion sheet vinyl flooring, VCT or cutback adhesive residue.
- Flextile waterproofing, crack-isolation and sound reduction membranes.
*For commercial exterior wall installations use Flextile 51 / 44 or Flextile 58XT systems.

FEATURES

- Excellent flexibility and bond strength.
- Excellent workability.
- Easy to use - just mix with water and apply.
- Water resistant when cured.
- Rated as a light performance commercial and residential mortar by ASTM C627-70 on plywood substrates.
- Rated as suitable for extra heavy service by ASTM C627-70 on concrete substrates.

LIMITATIONS

- Do not use over particleboard, Masonite, chipboard, OSB or similar unstable materials.
- Do not use over cushioned resilient flooring, rubber, plastic, paint, asphalt, or plywood surfaces in wet areas.
- Do not use over single layer plywood floors. Use only on surfaces, which are maintained at a temperature above 10°C (50°F) and below 35°C (95°F) during application and for at least 72 hours after application.
- To use directly over gypsum-based patching or leveling substrates, mix with Flextile 43 Thin-Set Mortar Additive or Flextile 44 High Solids Thin-Set Mortar Additive, also, apply suitable primer before use.
- On exterior applications, protect from rain until thoroughly dried and protect from freezing for at least 14 days after installation.
- When installing light-colored stones and translucent marble, use Flextile 50 White.
- Installations over nonporous surfaces may require extended setting/curing times.

- Do not use for moisture-sensitive stone such as green marble, certain limestone and granite, agglomerate tiles, cultured marble or resin-backed tiles. Instead, use Flexepoxy 100 mortar.
- For installations subject to severe freeze/thaw conditions use Flextile two component systems.

LEED Points Contribution

MR Credit 5, Regional Materials*
IEQ Credit 4.1, Low-Emitting
Materials – Adhesives & Sealants
IEQ Credit 4.3, Low-Emitting
Materials – Flooring Systems
**May be eligible*

LEED Points
Up to 2 points

1 point

1 point

TECHNICAL DATA (at 23°C (73°F) and 50% humidity)

Exceeds ANSI A118.4 and A118.11 specification requirements

| Description | ANSI SPEC. MPa (psi) | TYPICAL RESULT MPa (psi) |
|--|-------------------------|-----------------------------|
| 28 Day Shear Strength | | |
| Glazed Wall Tile | > 2.07 (300) | 2.93 to 4.14 (425 to 600) |
| Impervious Ceramic Tile (Porcelain) Mosaics | > 1.38 (200) | 2.24 to 3.11 (325 to 450) |
| Quarry Tile | > 1.03 (150) | 2.42 to 3.45 (350 to 500) |
| Quarry Tile / Plywood | > 1.03 (150) | 1.38 to 1.79 (200 to 260) |

Typical Physical Properties

| Description | |
|---------------|---|
| Pot Life | 2 hours |
| Open Time | 20 mins. |
| Initial Cure | 24-48 hrs. |
| Final Cure | 28 days |
| Cleanability: | with water before material dries |
| VOCs | 0 g/L |
| Shelf Life: | 1 year from production date when stored in dry, heated conditions |

Approx. coverage per 22.7 kg (50 lb) bag:

5mm (3/16") notched trowel - 10.0 M² (105 ft²)
6mm (1/4") notched trowel - 7.1 M² (77 ft²)
10mm (3/8") notched trowel - 5.5 M² (60 ft²)

** Coverages given are for estimating purposes only. Actual coverages may vary depending on job site conditions and installation techniques used.*

For job specific installation systems, recommendations, project warranty information, or for assistance with installation specifications, please contact Flextile's technical department.

Toronto, ON – Email: mzerey@flextile.net

Montreal, QC – Email: mzerey@flextile.net

Burnaby, BC – Email: mboldt@flextile.net

Toll Free 1-800-699-3623

Toll Free 1-800-699-3623

Toll Free 1-888-236-4486

Tel 1-416-255-1111

Tel 1-514-345-8666

Tel 1-604-420-4914

Fax 1-416-255-1729

Fax 1-514-345-8825

Fax 1-604-420-0936

INSTALLATION

PREPARATORY WORK

Surfaces must be sound, even, dry and free of grease, oil, dirt, paint, curing compounds or sealers, or other foreign matter. Surfaces must be true to a tolerance of 3 mm (1/8") in 2.4 meters (8 ft.) for walls and 6mm (1/4") in 3 meters (10 ft.) for floors. Concrete surfaces should have a wood float or steel trowel with broom finish. Roughen smooth concrete surfaces. Plywood floors should be designed for maximum deflection of 1/360 of span. This normally requires an overlay of 16 mm (5/8") exterior grade plywood over 25 mm (1") nominal boards or 16 mm (5/8") plywood when on joists 40 cm (16") O.C. Fasten overlay with screw type nails and glue where possible. Leave a 3 mm - 6 mm (1/8"-1/4") gap between sheets of overlay and next to all vertical surfaces to allow for expansion. Refer to current editions of TTMAC 09 30 00 Tile Installation Manual, or TCNA Handbook For Ceramic Tile Installation for information regarding placement of expansion or control joints, or for further substrate acceptability information.

APPLICATION

Mix with approximately 5 liters (1.3 US gallons) of water per 22.7 kg (50 lb) bag. Avoid using high-speed mixers.

Allow mixed mortar to slake for at least 10 minutes, then re-mix without adding further water. Spread a thin layer of mixed mortar with flat side of trowel to wet out the substrate; then re-apply sufficient material with a suitable notched trowel that will leave enough mortar to give at least 95% coverage to the backs of tile. Back buttering of tile is recommended for porcelain tile, high lugged tile, ungauged slate, stone, etc. and for all exterior applications. Comb that area which can be covered with tile before skinning occurs. Mortar should be troweled with notches running in straight lines so as to achieve maximum coverage. Press or beat in tile to achieve a finished thickness of mortar of at least 3mm (1/8") for thin-set applications. Do not adjust tiles after they have been set for more than 25 minutes.

CURING AND GROUTING

Protect from all traffic and delay grouting until cured at least 24 hours, and preferably 48 hours.

On exterior or cold weather applications, or when an impervious tile is installed over an impervious membrane, extended curing is recommended to ensure that mortar is sufficiently cured prior to grouting. Do not allow heavy traffic for at least 5 days following installation, and protect installation with 13 mm (1/2") plywood sheets prior to allowing construction equipment such as scissor lifts, etc. for a minimum of 7 days. Grout using Flextile Polymer Modified Grout or Flextile FlexEpoxy100 100% Solids Epoxy Grout, or Flextile ColourMax Plus Pre-Mixed Urethane Grout.

CAUTION

Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid extended contact with skin where possible and wash exposed skin areas promptly with water. If any cement or cement mixtures get into the eye, rinse immediately and repeatedly with water and get prompt medical attention. Keep out of reach of children.

SAFETY

Refer to Flextile Material Safety Data Sheet for detailed health and safety information.

AVAILABILITY AND COSTS

Flextile 50 Professional-Grade Polymer-Modified Mortar is available from Flextile Ltd. and its distributors in 22.7 kg (50 lb) bags.

Cost: Data supplied upon request.

WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price.

MAINTENANCE

No maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

RELATED REFERENCES

Current editions of TTMAC 09 30 00 & TCNA Ceramic Tile Installation Manuals.

February 21, 2013

