

100

FLEX-EPOXY 100% SOLIDS EPOXY MORTAR & GROUT

CHEMICAL RESISTANCE CHART

CHEMICAL	PROLONGED EXPOSURE	INTERMITTENT EXPOSURE	NOT RECOMMENDED
5% Acetic Acid		✓	
10% Acetic			✓
Ammonium Hydroxide	✓		
30% Ammonium Chloride	✓		
40% Ammonium Nitrate	✓		
40% Ammonium Sulfate	✓		
Sodium Hypochlorate- 6.5% act C1	✓		
Boric Acid	✓		
Butyl Alcohol		✓	
Calcium Chloride	✓		
Caustic Soda-50%	✓		
Caustic Potash-50%	✓		
10% Citric Acid		✓	
Diesel Fuel	✓		
Formaldehyde		✓	
10% Formic Acid		✓	
Glycerol	✓		
10% Hydrochloric Acid	✓		
30% Hydrogen Peroxide	✓		
Iron Chloride	✓		
Isopropyl Alcohol	✓		
Gasoline	✓		
Methylene Chloride			✓
Mineral Spirits	✓		
10% Nitric Acid		✓	
Olive Oil	✓		
10% Oxalic Acid	✓		
Perchloroethylene		✓	
50% Phosphoric Acid	✓		
Sodium Chloride	✓		
50% Sodium Hydroxide	✓		
10% Sulfuric Acid	✓		
96% Sulfuric Acid			✓
10% Tannic Acid	✓		
Toluene			✓
Trichlorethane			✓
Turpentine	✓		
Xylene			✓

July 23, 2013



Construction
Specifications
Canada

Devis de
Construction
Canada



For job specific installation systems, recommendations, project warranty information, or for assistance with installation specifications, please contact Flextile's technical department.

Toronto, ON – Email: mzerey@flextile.net

Toll Free 1-800-699-3623

Tel 1-416-255-1111

Fax 1-416-255-1729

Montreal, QC – Email: mzerey@flextile.net

Toll Free 1-800-699-3623

Tel 1-514-345-8666

Fax 1-514-345-8825

Burnaby, BC – Email: mboldt@flextile.net

Toll Free 1-888-236-4486

Tel 1-604-420-4914

Fax 1-604-420-0936

www.flextile.net