

100

FLEX-EPOXY 100% SOLIDS EPOXY GROUT

BASIC USES

For grouting all types of ceramic tile, quarry tile, pavers, granite, slate, mosaics or brick where superior stain resistance, chemical resistance, and high strength and impact resistance is required. For joint widths of 3 mm (1/8") to 15 mm (3/8").

COMPOSITION AND MATERIALS

An easy to use 100% solids, two-component cold water washable epoxy grout, consisting of two primary components; a hardening resin and a pre-mixed portion of epoxy resin, colour pigments and graded aggregate. Optional non-sag additive included where required.

FEATURES

- Superior stain resistance.
- Easy to mix and apply.
- Exceptional colour consistency.
- Ultra strong.
- Easy cold water clean-up.
- Non-sag filler supplied for vertical applications.

LIMITATIONS

Use only on surfaces maintained at a temperature of 15°C (60°F) to 35°C (95°F) during application and while curing. Cured Flex-Epoxy 100 will resist dry temperature up to 100°C (212°F) but should not be used in areas subject to excessive heat and moisture combined, such as steam rooms, etc. Not recommended for grouting light coloured marble. Some types of tile with surface porosity may require pre-sealing prior to grouting. For exterior applications consult Flextile Technical Service. Light coloured epoxy grouts should not be used in areas where continuous exposure to Ultraviolet rays exists.

LEED Points Contribution

MR Credit 5, Regional Materials*

IEQ Credit 4.1, Low-Emitting

Materials - Adhesives & Sealants

IEQ Credit 4.3, Low-Emitting

Materials - Flooring Systems

*May be eligible

LEED Points

Up to 2 points

1 point

1 point

TECHNICAL DATA

Exceeds ANSI A118.3 requirements

Typical Physical Properties

| | |
|--------------------------|---|
| Pot Life | 1-1.5 hours |
| Water Clean-up | 1.5 hours (@22°C (75°F)) |
| Initial Cure | 24 hours |
| Final Cure | 7 days |
| Tensile Strength | 8.4 MPa (1220 psi) |
| Compressive Strength | 60.0 MPa (8700 psi) |
| Shore D Hardness (24 hr) | 85 |
| Linear Shrinkage | 0% |
| Specific Gravity (paste) | 1.40 |
| Cleanability: | with water before material dries |
| Shelf Life: | 1 year from production date when stored at room temperature |

Approximate Grout Coverage: refer to Grout Calculator at flextile.net

[Grout Calculator Link](#)



Certified VOC-Free
USGBC LEED v4, BD&C, ID&C



■ INSTALLATION

PREPARATORY WORK

Ceramic tile surfaces must be clean and setting materials must be adequately cured prior to grouting. Remove spacers and rake out high ridges of setting material from tile joints prior to grouting to ensure uniform grout thickness. Tile joints must be clean and free of dirt, dust or other foreign matter prior to grouting. Do a test patch to see if pre-sealing of tile is required to avoid staining of the tile.

APPLICATION

Store Flex-Epoxy 100 at 20°C (68°F) for 12 hours prior to use. If the Flex-Epoxy is stiff or appears partially crystallized, heat unopened unit in hot tap water for approximately 20 minutes and then let material return to room temperature prior to use.

Mix Flex-Epoxy 100 by pouring all of Part B into Part A container. Mix using a slow speed mixer. Scrape bottom and sides of container to ensure Part B is thoroughly blended into all of Part A. For vertical applications, or for wider tile joints where epoxy grout may slump, mix in part or all of the non-sag additive provided to produce the desired working consistency. Wear rubber gloves and safety goggles. Avoid skin contact.

Using a solid, hard rubber float, force the mixer grout into tile joints working in a diagonal direction. Eliminate all gaps and voids and finish flush to the edge of square-edged tiles. Hold the float at 90° to the tile surface and use it to scrape excess epoxy grout from the face of the tiles. Within 1 hour after application of grout, clean the surface of the tile with cheesecloth or a cleaning pad and cool clean water. Rinse cleaning pad frequently to avoid re-depositing the residue on the tile surface. Ensure that the tile surface is properly cleaned before any residue can cure. Do not allow wash water to run into un-grouted tile joints. Avoid leaving any excess water on the surface of grout joints during clean-up, as this can affect the epoxy grout's cure.

■ CURING

Floors may receive some light foot traffic after 24 hours but should be protected from general traffic and routine cleaning operations for at least 72 hours, or until grout is hard and tack free. Protect from chemical exposure for 21 days.

■ CAUTION

Avoid skin contact. Wear rubber gloves and protective clothing. Wash hands frequently with soap and water and before breaks or eating. Remove and wash contaminated clothing. Keep out of reach of children.

■ SAFETY

Refer to Flextile Safety Data Sheet for detailed health and safety information available at flextile.net

■ AVAILABILITY

Flex-Epoxy 100 – 100% Solid Epoxy Grout is available from Flextile Ltd. and its distributors in 3.8 liter (1 US gallon) containers. Each container consists of; Part A epoxy resin / aggregate mixture, Part B hardener, and a separate portion of non-sag additive for use on vertical applications.

■ WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price.

■ MAINTENANCE

No maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

■ TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

■ RELATED REFERENCES

Current editions of TTMAC 09 30 00 & TCNA Ceramic Tile Installation Manuals.



Notice: The information herein is the best information we have relating to our products and the recommended uses of our products are based on tests believed to be reliable. Flextile warrants each of its products is of merchantable quality and suitable for the purpose for which it is intended BUT DOES NOT MAKE ANY OTHER WARRANTY, EXPRESS OR IMPLIED. This Warranty may not be enlarged or extended by our sales representatives, written sales information or drawings. Liability of Flextile under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price. All advice given and structural specifications supplied by Flextile representatives shall be used at the sole risk of those receiving the same and Flextile assumes no responsibility for the design or construction of any works in which its products are used. Any review or inspection of plans, buildings or product applications by Flextile representatives is not to be construed as approval thereof by Flextile. This information supersedes all previous issues and is subject to change without notice.