

53

FLOOR MIX THIN-SET MORTAR

DESCRIPTION

Flextile 53 is a dry-set mortar providing good bond strength with minimal shrinkage. Select quality blend of Portland cement, mineral fillers and special additives providing ease of application, good open time and adjustability.

BASIC USES

- Installation of quarry tile, pavers, ceramic mosaics and most other types of non-absorptive or vitreous ceramic tile.
- For installation of porcelain tile mix with Flextile 43 Thin-Set Mortar Additive or Flextile 44 High Solids Thin-Set Mortar Additive.

RECOMMENDED SURFACES

- Fully cured concrete floors.
- Installation over cement mortars and leveling compounds.
- For exterior installations, for installation of tile over exterior grade plywood surfaces (dry interior areas only), cement backer boards, over impervious membranes and existing surfaces of properly prepared non-cushion sheet vinyl flooring, VCT or cutback adhesive residue mix with Flextile 43 Thin-Set Mortar Additive or Flextile 44 High Solids Thin-Set Mortar Additive.

FEATURES

- High cement content.
- Excellent workability.
- Water resistant when cured.

LIMITATIONS

- Do not use for wall installations, use Flextile 51 for all vertical installations.
- Do not use over particleboard, Masonite, chipboard, OSB or similar unstable materials.
- Do not use over cushioned resilient flooring, rubber, plastic, paint, asphalt, or plywood surfaces in wet areas, or on single layer plywood floors.
- Use only on surfaces which are maintained at a temperature above 10°C (50°F) and below 35°C (95°F) during application and for at least 72 hours after application.
- For exterior applications, mix with Flextile 44 or Flextile 43 latex additives, protect from excessive moisture until thoroughly dried and protect from freezing for at least 14 days after installation.
- To use directly over gypsum-based patching or leveling substrates, mix with Flextile 43 Thin-Set Mortar Additive or Flextile 44 High Solids Thin-Set Mortar Additive, also, apply suitable primer before use.
- Do not use for moisture-sensitive stone such as green marble, certain limestone and granite, agglomerate tiles, cultured marble or resin-backed tiles. Instead, use Flexepoxy 100 mortar.

LEED Points Contribution

MR Credit 5, Regional Materials*
 IEQ Credit 4.1, Low-Emitting Materials – Adhesives & Sealants
 IEQ Credit 4.3, Low-Emitting Materials – Flooring Systems
 *May be eligible

LEED Points

Up to 2 points
 1 point
 1 point

TECHNICAL DATA at 23°C (73°F) and 50% humidity)

Exceeds A118.1 specification requirements

Description	ANSI SPEC.	TYPICAL RESULT
28 Day Shear Strength	MPa (psi)	MPa (psi)
Glazed Wall Tile	> 1.73 (250)	1.73 to 2.42 (250 to 350)
Impervious Ceramic Tile (Porcelain) Mosaics	> 1.04 (150)	1.21 to 1.38 (175 to 200)
Quarry Tile	> 1.04 (150)	1.73 to 2.07 (250 to 300)

Typical Physical Properties	
Pot Life	2 hours
Open Time	20 minutes
Initial Cure	24-48 hours
Final Cure	28 days
Cleanability:	With water before material dries
VOCs	0 g/L
Shelf Life:	1 year from production date when stored in dry, heated conditions

Approx. coverage per 22.7 kg (50 lb) bag:
 5 mm (3/16") notched trowel - 10.0 m² (105 ft²)
 6 mm (1/4") notched trowel - 7.1 m² (77 ft²)
 10 mm (3/8") notched trowel - 5.5 m² (60 ft²)

** Coverages given are for estimating purposes only. Actual coverages may vary depending on job site conditions and installation techniques used.*



■ INSTALLATION

PREPARATORY WORK

Surfaces must be sound, even, dry and free of grease, oil, dirt, paint, curing compounds or sealers, or other foreign matter.

Surfaces must be true to a tolerance of 3 mm (1/8") in 2.4 meters (8 ft.) for walls and 6 mm (1/4") in 3 meters (10 ft.) for floors. New concrete should have a wood float or steel trowel with broom finish. Roughen smooth concrete surfaces. Refer to current editions of TTMAC 09 30 00 Tile Installation Manual, or TCNA Handbook for Ceramic Tile Installation for information regarding placement of expansion or control joints, or for further substrate acceptability information.

APPLICATION

Mix Flextile 53 Floor Mix by adding dry powder to approximately 5.5 Liters (1.5 U.S. gallons) of cool, clean water or Flextile 43 Thin-Set Mortar Additive, or Flextile 44 High Solids Thin-Set Mortar Additive. Avoid using high-speed mixers. Allow mixed mortar to slake for at least 10 minutes, then re-mix without adding further liquid. Resulting mortar should be of a thick, easily spreadable consistency. Spread a thin layer of mixed mortar with flat side of trowel to wet out the substrate; then re-apply sufficient material with a suitable notched trowel that will leave enough mortar to give at least 95% coverage to the backs of tile. Back buttering of tile is recommended for porcelain tile, large format or high lugged tile, ungauged slate, stone, etc. and for all exterior applications. Comb that area which can be covered with tile before skinning occurs. Mortar should be troweled with notches running in straight lines so as to achieve maximum coverage. Press or beat in tile to achieve a finished thickness of mortar of at least 3 mm (1/8"). Do not adjust tiles after they have been set for more than 25 minutes.

■ CURING AND GROUTING

Protect from all traffic and delay grouting until cured at least 24 hours, and preferably 48 hours. On exterior or cold weather applications, or when a larger format or impervious tile is installed over an impervious membrane, extended curing is recommended to ensure that mortar is sufficiently cured prior to grouting. Do not allow heavy traffic for at least 5 days following installation, and do not allow heavy construction equipment such as scissor lifts, etc. for a minimum of 14 days following installation. Protection of installation with 13 mm (1/2") plywood sheets prior to allowing heavy construction equipment is recommended until installation is fully cured. Grout using Flextile Polymer Modified Grout, Flextile 1600UPG Ultra Performance Grout or Flextile FlexEpoxy100 - 100% Solids Epoxy Grout.

■ CAUTION

Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid extended contact with skin where possible and wash exposed skin areas promptly with water. If any cement or cement mixtures get into the eye, rinse immediately and repeatedly with water and get prompt medical attention. Keep out of reach of children.

■ SAFETY

Refer to Flextile Safety Data Sheet for detailed health and safety information.

■ AVAILABILITY

Flextile 53 Floor Mix Thin-Set Mortar is available from Flextile Ltd. and its distributors in 22.7 kg (50 lb) bags.

■ WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price.

■ MAINTENANCE

No maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

■ TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

■ RELATED REFERENCES

Current editions of TTMAC 0930 00 & TCNA Ceramic Tile Installation Manuals.



Notice: The information herein is the best information we have relating to our products and the recommended uses of our products are based on tests believed to be reliable. Flextile warrants each of its products is of merchantable quality and suitable for the purpose for which it is intended BUT DOES NOT MAKE ANY OTHER WARRANTY, EXPRESSED OR IMPLIED. This Warranty may not be enlarged or extended by our sales representatives, written sales information or drawings. Liability of Flextile under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price. All advice given and structural specifications supplied by Flextile representatives shall be used at the sole risk of those receiving the same and Flextile assumes no responsibility for the design or construction of any works in which its products are used. Any review or inspection of plans, buildings or product applications by Flextile representatives is not to be construed as approval thereof by Flextile. This information supersedes all previous issues and is subject to change without notice.